

技术参数 Technical Data

产品代号 Product Code	克重 (g / m ²) Weight	拉伸断裂强力 N / 75mm Tensile Strength		可燃物含量 LOI(%)	含水率 (%) Moisture Content	层合板弯曲强度 (Mpa) Flexural Strength of laminated board	
		纵向 Longitudinal	横向 Lateral			标准状态 Standard	潮湿状态 Moisture
ECRMS300	300	≥ 135	≥ 40	2 ~ 8	≤ 0.2	≥ 144	≥ 125
ECRMS380	380	≥ 160	≥ 50	2 ~ 8	≤ 0.2		
ECRMS450	450	≥ 160	≥ 50	2 ~ 8	≤ 0.2		
ECRMS600	600	≥ 180	≥ 80	2 ~ 8	≤ 0.2		