

缠绕系列 Filament Winding Epoxy Series

品名 Product	混合黏度 Mixed Viscosity	操作期 Pot Life	外观颜色 Color	玻璃转化 温度 Tg	特性 Features
AF-4122A/B	500-1000	>6h	微黄透明 Yellowish Clear	> 120	玻纤制品韧性高 High-toughness for Glass Fiber Products
AF-4106A/B	500-1000	>6h		> 105	与碳纤结合性好、90° 拉伸强度高 Good Associativity to Carbon Fiber, Strong Tensile Strength at 90°
AF-4146A/B	800-1200	>6h		> 145	韧性好 Good Toughness
AF-4182A/B	600-1000	>6h	> 170		
AF-4080A/B	600-1000	>6h	黄色透明 Yellowish Clear	> 95	阻燃 Flame-retardant
AF-4900A/B	1000-1500	>6h	褐色 Brown	> 210	耐高温、韧性好 High heat-resistance and toughness
AF-4060A/B	500-1000	>6h	微黄透明 Yellowish Clea	> 110	酸酐类缠绕 Acid Anhydride Filament Winding
AF-4090A/B	300-400	>2h		> 60	胺类缠绕 Amine, Filament Winding
AF-8190A/B	300-550	140-220min		> 185	胺类固化, Tg190°C Amine Curing, Tg190°C