

## 通用型产品 General Epoxy Series

品名 Product	混合黏度 Mixed Viscosity	操作期 Pot Life	特性 Characteristics	推荐工艺 Recommended Processes
GE-7118 系列 ( Series )	200-300	75-180 min	低粘度真空灌注 Low Viscous Vacuum Infusion	真空灌注、RTM、小型制品缠绕 Vacuum Infusion, RTM, Small-sized Product Winding
GE-7119 系列 ( Series )	800-2000	10-80 min	手糊快速成型 Fast Curing Hand Lay-up	手糊层压、RTM、小型制品缠绕 Hand Lay-up Laminated, RTM, Small-sized Product Winding
TF-4122A/B	500-1000	>6 h	玻纤制品韧性高 High Toughness for Glass Fiber	缠绕, 拉挤, SMC, RTM Filament Winding, Pultrusion, SMC, RTM
TF-3128A/B	300-600	@150°C 90-110 second	拉挤稳定 Stable when Pultruded	
QC-360A/B	274	32 min	常温固化、无色透明 Curing at Room Temperature	真空灌注, 手糊层压, RTM, 小型制品缠绕 Vacuum Infusion, Hand Lay-up Laminated, RTM, Small-sized Product Winding
HT-723A/B-1	200-300	80-100 min	Tg125°C, 耐热稳定性高。	