

产品代号 Product Code	线密度偏差% Linear Density Tolerance	单纤维直径 $\mu\text{m}$ Filament of Diameter	断裂强度N / tex Tensile Strength	含水率% Moisture Con- tent	可燃物含量(% ) LOI	适用树脂 Compatible Resin
ECR200D	$\pm 5$	13	$\geq 0.4$	$\leq 0.1$	$0.55 \pm 0.10$	环氧树脂EP
ECR300D	$\pm 5$	13	$\geq 0.4$	$\leq 0.1$	$0.55 \pm 0.10$	环氧树脂EP
ECR600D	$\pm 5$	17	$\geq 0.4$	$\leq 0.1$	$0.55 \pm 0.10$	环氧树脂EP
ECR1200D	$\pm 5$	17	$\geq 0.4$	$\leq 0.1$	$0.55 \pm 0.10$	环氧树脂EP
ECR2400D	$\pm 5$	17	$\geq 0.4$	$\leq 0.1$	$0.55 \pm 0.10$	环氧树脂EP